

The main characteristics of Cyanolit® 201 are the low viscosity, the extremely short setting/bonding time and capillary attraction.

The material is very useful for small bonding joints and application. According to the construction the adhesive possible to be applied after the basic assembling.

The bonding time, depending on the material, varies from 5 to 20 seconds.

Shelf life:

Store in original, unopened containers for 6 months at 5-7°C

Technical Data

Color	transparent
Resin	Ethyl-2-Cyanacrylat
Gap Width max	0,05 mm

UNCURED PROPERTIES

Viscosity (Brookfield LVT/25°C) [mPa·s]	2
Flash point [°C]	> 83

Tensile Strength/SETTING TIME

PVC hart	7 seconds	* 5,5 MPa
ABS	12 seconds	* 5,4 MPa
PA 6.6	20 seconds	4,3 MPa
PVC/Stahl	15 seconds	* 7 MPa
Alu/ABS	15 seconds	* 5 MPa

*material breakage

CURED PROPERTIES

Temperature Resistance	-80 to 80 °C
------------------------	--------------

Our data sheets have been compiled to the best of our knowledge. The information included in our data sheets is exclusive information for the intended user and describes characteristics, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For an additional technical consultation, please contact our RD department. In general, for guarantee claims, please refer to our standard terms and conditions.

**Adhesives
and more...**